

ALUBEN EP MOLY GREASE

Multipurpose Aluminum Complex Grease

General Description

Aluben EP Moly is a high quality multipurpose grease available in NLGI grades 1 and 2 that is recommended for agriculture, automotive, construction and industrial applications.

Aluben EP Moly is a top quality aluminum complex thickened grease with molybdenum disulfide ("moly") and a premium additive system combined to give outstanding performance in a broad range of operating conditions. This grease provides excellent high temperature performance, both in oxidation resistance and resistance to oil separation. Shock load carrying capability is optimized with the use of moly, providing excellent performance in industrial, commercial and construction equipment applications. Aluben EP Moly Grease offers good water washout and water spray-off protection for applications that are in wet environments.

Expect Excellent Performance in:

- Extreme pressure conditions
- High shock load environments
- High humidity conditions
- Chassis lubrication
- Wheel bearings
- General greasing

Features and Benefits

Water Resistance: The thickener type and tacky additive provide excellent water resistance.

Extreme Pressures: The moly and EP additives provide superior ability to withstand high loads and high shock loading.

High Temperature Performance: Excellent drop point and oxidation resistance provide long lubricant life and stability at high temperatures.

Typical Application

Aluben EP Moly is recommended where the equipment manufacturer recommends:

- Multipurpose #2 or #1 EP grease
- General chassis type lubricant
- Molybdenum disulfide ("moly") fortified grease

Typical Customer

- Agricultural Equipment Operators & Shops
- Industrial Equipment Operators
- Truck Service Shops
- Auto Service Shops

PDS-H11-02

ALUBEN EP MOLY GREASE

Multipurpose Aluminum Complex Grease

Typical Properties

NLGI Grade	2	1
Soap Type	Aluminum Complex	Aluminum Complex
Additives Present	R&O, EP & AW	R&O, EP & AW
Color	Gray/Black	Gray/Black
Texture	Smooth	Smooth
Dropping Point, °F	475 Min.	475 Min.
Worked Penetration	280	325
Mineral Oil & Soluble Additives		
Viscosity @ 40°C, cSt	200	200
Viscosity @ 100°C, cSt	15.5	15.5
Timken OK Load, lb., min.	45	45

The typical properties listed reflect the general characteristics of the product, and are not manufacturing specifications. Normal batch-to-batch variations should be expected.

Health & Safety

A complete material safety data sheet is available upon request. Avoid prolonged or repeated skin contact. Wash clothing and exposed areas with soap and water. Don't pollute.